



# PLIBRICO COMPANY

1800 N. Kingsbury Street  
 Chicago, IL 60614  
 Ph. : (773) 549-7014 Fax : (773) 549-0424  
 Web : www.plibrico-usa.com

# REFRACTORY PRODUCT DATA SHEET

Data date: 1/6/00

## PLISTIX INJEC-TITE LWI 2300

Product # 17618

### Product Description:

A ceramic fiber based, insulating refractory injection mix.

<b>Max. Service Limit::</b>	2300 F / 1260 C	<b>Density:</b>	<b>To Place</b>	<b>In Service</b>
			75 pcf	30 pcf
			1201 kg/m <sup>3</sup>	480 kg/m <sup>3</sup>
<b>Packaging:</b>	50 lb / 22.7 kg Pail			
<b>Required Water:</b>	qt. / 0 l per bag	<b>Min. Time Before Firing:</b>	None	

### Chemistry - % (calcined)

Al <sub>2</sub> O <sub>3</sub>	19	CaO	0.1	SiC
SiO <sub>2</sub>	77.8	MgO	0.3	ZrO <sub>2</sub>
Fe <sub>2</sub> O <sub>3</sub>	1.6	Alk.	1.1	Other
TiO <sub>2</sub>	0	P <sub>2</sub> O <sub>5</sub>		

### Abrasion Loss

(ASTM C704)  
 1500 F / 815 C  
 cc

### Thermal Conductivity

	btu*in/hr*ft <sup>2</sup> *F	w / m*C
500 F / 260 C	1	0.1
1000 F / 540 C	1.2	0.2
1500 F / 815 C	1.3	0.2
2000 F / 1095 C		0

Temperature	Linear Change - % ASTM C113	Cold MOR psi / MPa ASTM C133	Hot MOR psi / MPa ASTM C583	CCS psi / MPa ASTM C133
		0		0
2300 F / 1260 C	-3.2	0	0	0
		0	0	0
		0	0	0
		0	0	0
		0	0	0

Bake out:

ASTM classification:

Note: Data should not be used for specification purposes. Product data is periodically updated to reflect product / raw material / process changes. Please consult with your Pibrico representative to insure you have the most current data.

All data are averaged results of laboratory ASTM tests on laboratory cast specimens. Reasonable variations can be expected.

Thermal conductivity will vary depending upon measurement method, installed density, and thermal treatment.

Registered trademarks of Plibrico Company include: PLISTIX, INJEC-TITE, & LWI